CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-08-09-01** **Date: 11-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-17
Sample ID No	:	2017-08-09-01/01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	10-08-17

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	3.12	–
2	Finess by Air permeablity method (m^2/kg, Min)	268.68	225m^2/kg, Min
3	Density (gm/cc)	3.17	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	165 minutes	Not less than 30 minutes
6	Final Setting time	270 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

AE Ward no 5

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2017-08-09-01** **Date: 07-09-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-17
Sample ID No	:	2017-08-09-01/01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	10-08-17

Compressive Strength			
Sl.No.	**Physical properties**	**Results**	**Requirement as per IS 12269: 2013**
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	54.5N/mm^2	Not less than 53 N/mm^2

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-08-09-01** **Date: 12-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	09-08-17
Sample ID No	:	2017-08-09-01/02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	09-08-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	342	342	2.3	97.7	90-100
3	20 mm	5780	6122	40.8	59.2	30-70
4	10 mm	4253	10375	69.2	30.8	10-35
5	4.75 mm	4222	14597	97.3	2.7	0-5
6	Pan	403	15000	100.0	0	---

AE ward No 5

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-08-09-01** **Date: 12-08-17**

Sample ID No : 2017-08-09-01/02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**12.6**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.5**	
3	Specific Gravity	**2.69**	_
4	Bulk Density(Loose) (Kg/l)	**1.57**	_
5	Bulk Density(Compacted) (Kg/l)	**1.61**	_
6	Water Absorption(%)	**0.22**	_

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2017-08-09-01** **Date: 12-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-17
Sample ID No	:	2017-08-09-01/02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	09-08-17

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	322	322	6.4	93.6	90-100
3	10 mm	2543	2865	57.3	42.7	25-55
4	4.75 mm	1890	4755	95.1	4.9	0-10
5	Pan	245	5000	100	0	–

AE ward no 5

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2017-08-09-01** **Date: 12-08-17**

Sample ID No : 2017-08-09-01/02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**12.4**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.8**	
3	Specific Gravity	**2.69**	–
4	Bulk Density(Loose) (Kg/l)	**1.49**	–
5	Bulk Density(Compacted) (Kg/l)	**1.53**	–
6	Water Absorption(%)	**0.21**	–
7	Aggregate crushing Value(%)	**24.2**	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	**23.6**	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF FINE AGGREGATE

Lab ID	:	**CP-2017-08-09-01** **Date: 12-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-08-17
Sample ID No	:	2017-08-09-01/03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	09-08-17
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	80	80	8.0	92.0	90-100	90-100	90-100	95-100
3	2.36 mm	134	214	21.4	78.6	60-95	75-100	85-100	95-100
4	1.18 mm	166	380	38.0	62.0	30-70	55-90	75-100	90-100
5	600 micron	187	567	56.7	43.3	15-34	35-59	60-79	80-100
6	300 micron	177	744	74.4	25.6	5-20	8-30	12-40	15-50
7	150 micron	165	909	90.9	9.1	0-10	0-10	0-10	0-15
8	Pan	91	1000	100.0	0.0	---	---	---	---
Result :The tested Sample Conforms to Grading Zone II									

CIVIL Pro Sig..... Date..... BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2017-08-09-01** **Date: 12-08-17**

Sample ID No : 2017-08-09-01/03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.85	–
2	Specific Gravity	2.56	–
3	Material finer than 75 micron(%)	4.8	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE ward No 5

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST RESULTS OF STEEL

Lab ID	:	**CP-2017-08-21-01** **Date: 22-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-08-17
Sample ID No	:	2017-08-21-01/04
Sample Type	:	JSW
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	21-08-17

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	JSW	Fe500	8	0.390	542	660	20.0%	Satisfactory	Satisfactory
2	JSW	Fe500	10	0.614	565	680	19.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE Ward No 5

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2017-08-15-04**	**Date: 19-08-17**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.	
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.	
Agency	:	Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.	
Customer's Reference	:	BBMP/EE/BTP/WO/99/2017-18	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	15-08-17	
Sample ID No	:	2017-08-15-04/01	
Sample Type /Size	:	Precast Cover Slab	
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete	
Date of test	:	15/08/2017	

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(mm)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.283	4477	100.9	22.5	21.0	26.2
2	Cover Slab-2	75.49	100.52	1.322	4475	98.3	22.0	20.4	25.5
3	Cover Slab-3	75.50	100.51	1.318	4476	94.5	21.1	19.6	24.5

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE ward No.5

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM,. BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-07-26-02** **Date: 29/08/2017**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.

Agency : Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.

Customer's Reference : BBMP/EE/BTP/WO/99/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-07-17

Sample ID No : 2017-07-26-02/01

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/08/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	22/08/2017	29/08/2017	150.34 X 150.37 X 150.25	22607	8.267	388.8	17.2	17.1
2	PCC	M20	22/08/2017	29/08/2017	150.43 X 150.39 X 150.40	22623	8.289	391.4	17.3	
3	PCC	M20	22/08/2017	29/08/2017	150.37 X 150.31 X 150.28	22602	8.243	379.7	16.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE ward No5

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-07-26-02** **Date: 02/09/2017**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.

Agency : Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.

Customer's Reference : BBMP/EE/BTP/WO/99/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-07-17

Sample ID No : 2017-07-26-02/02

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 11 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 02/09/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M20	22/08/2017	02/09/2017	150.45 X 150.39 X 150.42	22626	8.259	459.3	20.3	20.7
2	PCC	M20	22/08/2017	02/09/2017	150.48 X 150.45 X 150.41	22640	8.267	473.2	20.9	
3	PCC	M20	22/08/2017	02/09/2017	150.38 X 150.33 X 150.36	22607	8.272	470.2	20.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE ward no 5

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: T- 4358

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-08-26-02** **Date: 31/08/2017**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.

Agency : Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.

Customer's Reference : BBMP/EE/BTP/WO/99/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-07-17

Sample ID No : 2017-07-26-02/03

Customer ID : Drain Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	24/08/2017	31/08/2017	150.25 X 150.29 X 150.21	22581	8.266	388.4	17.2	17.5
2	Drain Concrete	M20	24/08/2017	31/08/2017	150.24 X 150.22 X 150.34	22569	8.287	395.0	17.5	
3	Drain Concrete	M20	24/08/2017	31/08/2017	150.24 X 150.29 X 150.33	22580	8.289	404.2	17.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-08-26-02** **Date: 04/09/2017**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.

Agency : Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.

Customer's Reference : BBMP/EE/BTP/WO/99/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-07-17

Sample ID No : 2017-07-26-02/04

Customer ID : Drain Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 11 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 04/09/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	24/08/2017	04/09/2017	150.42 X 150.34 X 150.36	22614	8.287	470.4	20.8	20.9
2	Drain Concrete	M20	24/08/2017	04/09/2017	150.29 X 150.25 X 150.22	22581	8.294	481.0	21.3	
3	Drain Concrete	M20	24/08/2017	04/09/2017	150.32 X 150.34 X 150.36	22599	8.276	463.3	20.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE ward No.5

CIVIL Pro Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2017-08-26-02** **Date: 31/08/2017**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to road and Drains at Jakkur Extension in ward No.05 Byatarayanapura Sub Division.

Agency : Narasimharaju K, #175, 5th Cross, Bhadrappa layout, Nagashetyhalli, Bangalore-560094.

Customer's Reference : BBMP/EE/BTP/WO/99/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-07-17

Sample ID No : 2017-07-26-02/05

Customer ID : Drain Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2017

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	24/08/2017	31/08/2017	150.29 X 150.30 X 150.31	22589	8.297	397.6	17.6	17.3
2	Drain Concrete	M20	24/08/2017	31/08/2017	150.35 X 150.31 X 150.37	22599	8.286	393.2	17.4	
3	Drain Concrete	M20	24/08/2017	31/08/2017	150.25 X 150.29 X 150.22	22581	8.287	381.6	16.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

AE Ward no 5

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****